

**TEKNİK BİLGİ FORMU****KA01G2075  
ANTİKOROZİF ASTAR**

**Ürün Tanımı** Modifiye alkid reçineleri içeren, hava kurumalı antikorozif astardır. Metal sanayinin, yüksek korozyon dirençli ve hızlı kurumalı boya talebini karşılamak üzere geliştirilmiştir.

**Ürün Özellikleri**

Renk	Açık Gri (RAL 7035)
Katı Madde (hacmen)	% 44 ± 3
VOC (uçucu organik madde)	490 gr/lt
Teorik kaplama alanı	1 kg boya ile 50 mikron kuru film bırakacak şekilde tatbik edildiğinde yaklaşık 6 m <sup>2</sup> alan kaplanır.
Pratik kaplama alanı	Yüzey pürüzlülüğü ve sıçrıntı kayıpları nedeniyle kesin bir değer verilemez. Aşağıdakiler yaklaşık değerler olarak alınabilir: Büyük parçalar için : % 70 x Teorik kaplama alanı Küçük parçalar için : % 50 x Teorik kaplama alanı

**Uygulama Bilgileri**

Uygulama metodu	Sprey
Uygulama viskozitesi, 20°C	18 ± 2 sn. / DIN CUP 4
Karışım oranı	Tiner (TK0001) : %10-15 ağırlıkça
Kuruma koşulları, %65 RH	Toz Kuruma : 4-10 dak. / 20°C Dokunma Kuruma : 12-20 dak. / 20°C Tam Kuruma : 6-7 gün / 20°C
Uygulama sıcaklığı, %65 RH	5°C - 45°C
Uygulama kalınlığı	50 ± 5 mikron kuru film.
Yüzey hazırlığı	Boyanacak yüzey her türlü yağ, kir, toz ve nemden arındırılmış olmalıdır.

**Depolama ve Güvenlik Bilgileri**

Depolama Süresi	Orijinal ambalajının açılmaması durumunda 5°C - 40°C sıcaklıklar arasında, normal stoklama koşullarında en az 6 ay süreyle depolanabilir.
Uyarılar	Etiket üzerindeki uyarılara bakınız. Taşınması, depolanması ve atıklarının yok edilmesi sırasında, ilgili yasa ve tüzüklere uyulmalıdır. Detaylı bilgi için Güvenlik Bilgi Formu' na başvurunuz.

Sistemlerimizin etkinliği, laboratuvar araştırmaları ve yıllar süren pratik tecrübelerimiz üzerine kurulmuştur. Ürünler talimatlara göre ve iyi bir işçilikle uygulandığında, ortaya çıkan işin kalitesinin Kansai Altan standartlarına uygun olacağı tarafımızdan garanti edilmektedir. Ancak, elde edilen sonucun kontrolümüz dışında olan faktörlerce etkilenmesi durumunda sorumluluk kabul edilmez. Müşteri, satın aldığı ürünlerin söz konusu uygulamaya uygun olup olmadığını, normal olarak sahip olması gereken yöntemlerle kontrol etmek durumundadır.

**TECHNICAL DATA SHEET****KA01G2075**  
**ANTICORROSIVE PRIMER**

**Product Description** Air-drying anticorrosive primer based on modified alkyd resins. Meets the demands of metal industry for high corrosion resistance and quick drying property.

**Paint Properties**

**Color** Light Grey (RAL 7035)

**Solids (by volume)** % 44 ± 3

**VOC (volatile organic compound)** 490 g/lit

**Theoretical coverage** Approximately 6 m<sup>2</sup> / 1 kg paint for 50 microns dry film thickness.

**Practical coverage** The practical coverage depends on the factors, such as shape of the construction, roughness of the substrate, method and conditions of application. A guideline for spraying is:  
Large areas : Approx. 70% of the theoretical coverage.  
Small areas : Approx. 50% of the theoretical coverage.

**Application Information**

**Application method** Spray

**Application viscosity, 20°C** 18 ± 2 sec. / DIN CUP 4

**Mixing ratio** Thinner (TK0001): 10-15% by wt.

**Drying conditions, 65% RH**  
Dust Dry : 4-10 min. / 20°C  
Touch Dry : 12-20 min. / 20°C  
Hard Dry : 6-7 days / 20°C

**Application temperature, 65% RH** 5°C - 45°C

**Film thickness** 50 ± 5 microns dry film.

**Surface preparation** All surfaces to be coated should be clean, dry and free from contaminations.

**Storage and Safety Information**

**Storage time** Minimum 6 months in unbroken original package at 5°C - 40°C.

**Warnings** See label for precautions. The user of this product is required to comply with the national statutory regulations for health, safety during transportation and at work and waste disposal. See the MSDS for detailed information.

The effectiveness of our systems is based on many years' practical experience and laboratory research. We guarantee that the quality of the work performed in accordance with our systems meets the Kansai Altan standards, provided that our instructions are followed carefully and the work is performed in accordance with the requirements as to good craftsmanship. We decline any responsibility, if the final result is affected by factors beyond our control. The customer has to determine the suitability of the delivered products for the intended application by using the means which normally are at his disposal.